

Product Data Sheet

Purolite® C100E

Strong Acid Cation Gel

Gel Strong Acid Cation Resin

Purolite C100E is a high purity premium grade bead form conventional gel polystyrene sulfonate cation exchange resin designed expressly for the treatment of foodstuffs, beverages, potable waters, and water used in the processing of food. Its specification is such that it will exceed the relevant EEC requirements, and the resin is in compliance with the U.S. Food & Drug Administration Code of Federal Regulations section 21, paragraph 173.25; for use in the treatment of foods for human consumption. Its high bead integrity, excellent chemical and physical stability, and very low extractibles content play a large part in its successful employment in these areas.

Typical Physical and Chemical Characteristics

BASIC FEATURES:

Application - Domestic/Industrial/Food grade softening - supplied in Na+ form - Potable Use

Polymer Structure - Gel polystyrene crosslinked with DVB

Appearance - Amber, clear spherical beads

Functional Group - Sulfonic acid

Ionic Form as Shipped - Na

PRODUCT INFORMATION:

Total Capacity (min.) 1.9 eq/l (41.5 Kgr/ft 3) (Na $^+$ form) Moisture Retention 46 - 50 % (Na $^+$ form) Particle Size Range 300 - 1200 μ m (max.) 1 % Uniformity Coefficient (max.) 1.7 Reversible Swelling Ca $^{2+} \rightarrow \text{Na}^+$ 8 % Reversible Swelling, Na $^+ \rightarrow \text{H}^+$ (max.) 10 % Specific Gravity 1.27 Shipping Weight (approx.) 800 - 840 g/l (50 - 52.5 lb/ft3) Temperature Limit 120°C (250°F)		
Particle Size Range $300 - 1200 \mu m$ $< 300 \mu m (max.)$ 1% Uniformity Coefficient (max.) 1.7 Reversible Swelling Ca ²⁺ \rightarrow Na ⁺ 8% Reversible Swelling, Na ⁺ \rightarrow H ⁺ (max.) 10% Specific Gravity 1.27 Shipping Weight (approx.) $800 - 840 g/l (50 - 52.5 lb/ft3)$	Total Capacity (min.)	1.9 eq/l (41.5 Kgr/ft ³) (Na ⁺ form)
<300 μ m (max.) Uniformity Coefficient (max.) Reversible Swelling Ca ²⁺ \rightarrow Na ⁺ Reversible Swelling, Na ⁺ \rightarrow H ⁺ (max.) Specific Gravity Shipping Weight (approx.) 1 % 10 % 800 - 840 g/l (50 - 52.5 lb/ft3)	Moisture Retention	46 - 50 % (Na ⁺ form)
Uniformity Coefficient (max.) 1.7 Reversible Swelling $Ca^{2^+} \rightarrow Na^+$ 8 % Reversible Swelling, $Na^+ \rightarrow H^+$ (max.) 10 % Specific Gravity 1.27 Shipping Weight (approx.) 800 - 840 g/l (50 - 52.5 lb/ft3)	Particle Size Range	300 - 1200 μm
Reversible Swelling $Ca^{2+} \rightarrow Na^{+}$ 8 % Reversible Swelling, $Na^{+} \rightarrow H^{+}$ (max.) Specific Gravity 1.27 Shipping Weight (approx.) 800 - 840 g/l (50 - 52.5 lb/ft3)	<300 µm (max.)	1 %
Reversible Swelling, Na ⁺ → H ⁺ (max.) Specific Gravity 1.27 Shipping Weight (approx.) 800 - 840 g/l (50 - 52.5 lb/ft3)	Uniformity Coefficient (max.)	1.7
Specific Gravity 1.27 Shipping Weight (approx.) 800 - 840 g/l (50 - 52.5 lb/ft3)	Reversible Swelling $Ca^{2+} \rightarrow Na^{+}$	8 %
Shipping Weight (approx.) 800 - 840 g/l (50 - 52.5 lb/ft3)	Reversible Swelling, $Na^+ \rightarrow H^+$ (max.)	10 %
	Specific Gravity	1.27
Temperature Limit 120°C (250°F)	Shipping Weight (approx.)	800 - 840 g/l (50 - 52.5 lb/ft3)
	Temperature Limit	120°C (250°F)

USA

Telephone: +1 610 668 9090 Fax: +1 610 668 8139 Email: <u>info@puroliteusa.com</u> Europe

Telephone: +44 1443 229334 Fax: +44 1443 227073 Email: <u>sales@purolite.com</u> Asia Pacific

Telephone: +86 571 876 31382 Fax: +86 571 876 31385 Email: <u>info@purolitechina.com</u>